

GEOMETRICAL CHARACTERISTICS AND LENGTHS OF BARE RUBBER THREADS
--

Count	Диаметр	Площадь	Плотность (Max)	Метров в 1 кг
	мм	поперечного сечения		
		(mm)2		
12	2.12	3.531	1.018	288
14	1.81	2.574	1.018	395
16	1.59	1.986	1.018	512
18	1.41	1.562	1.018	630
20	1.27	1.267	1.018	780
24	1.06	0.883	1.018	1120
26	0.977	0.749	1.018	1311
28	0.91	0.651	1.018	1520
30	0.85	0.568	1.018	1750
32	0.79	0.490	1.018	1990
34	0.75	0.442	1.018	2250
36	0.71	0.396	1.018	2520
38	0.67	0.353	1.018	2800
40	0.6350	0.322	1.018	3100
42	0.6048	0.283	1.018	3610
44	0.5773	0.264	1.018	3750
46	0.552	0.239	1.018	4104
48	0.529	0.220	1.018	4469
50	0.51	0.204	1.018	4850
52	0.49	0.189	1.018	5435

54	0.47	0.174	1.018	5660
56	0.454	0.161	1.018	6083
60	0.42	0.139	1.018	6990
63	0.403	0.128	1.018	7698
65	0.39	0.120	1.018	8200
70	0.36	0.102	1.018	9510
75	0.34	0.091	1.018	10920
80	0.32	0.080	1.018	12440
90	0.28	0.062	1.018	15740
Tolerance	± 3%	± 3%	± 5%	± 5%

--